

PRODUCT INFORMATION



Valvoline Performance Products – Tectyl

Version: TE071/02

Tectyl™ ML Greenline

Premium resin/oil based, corrosion preventive compound in aerosol

TECTYL ML Greenline is a resin/oil based, light brown/yellow, liquid corrosion preventive compound which is supplied in an aerosol spray can.

TECTYL ML Greenline is highly efficient with an advantageous environmental profile being almost completely free from organic solvent. Furthermore, application of the product generates almost no smell.

TECTYL ML Greenline is designed for industrial application, giving good penetration into folds, flanges and cracks, making it very suitable as a corrosion preventive for the inside of car doors and other hollow sections of cars and rolling equipment.

TECTYL ML Greenline cures to a light yellow, translucent, semi-soft film.

Approvals/Performance levels

Tectyl ML GREENLINE

Accelerated Corrosion tests:
@ Average recommended DFT

Accelerated Corrosion tests:
Salt Spray; 5 % NaCl @ 35°C; ISO 9227 NSS
(Q-Panels, Type R, ASTM A1008)
15+ days

Humidity; 100 % RH; @ 40°C; ISO 6270-2 CH
(Q-Panels, Type R, ASTM A1008)
50+ days

Estimated Protection Period

Indoor: 18 months

TECTYL ML Greenline is Approved according to TR 338:2010, **SFS 4086:2006**, 02-12-2010; Granted certificate by Inspecta Sertifionti Oy for Anti-corrosion agents for internal hollow.

Surface Preparation:

The maximum performance of **TECTYL ML GREENLINE** can be achieved only when the metal surfaces to be protected are clean, dry and free of rust, oil and mill scale and a substrate temperature of 10-35 °C at the time of product application.

Application:

TECTYL ML GREENLINE gives a maximum performance when it is sprayed at an ambient and product temperature of 10-25 °C. Shake the can with **TECTYL ML GREENLINE** well before use and spray at a distance of approximately 25 cm from the surface. As the **TECTYL ML GREENLINE** is a fast drying product this can cause “pin-holing” when the product is applied too thick at once. Valvoline advises to spray one layer per pass, wait for 2 to 3 minutes and then spray another layer. Continue like this until the required film thickness has been obtained. **DO NOT FREEZE TECTYL ML GREENLINE.**

Removal:

TECTYL ML GREENLINE can be removed with mineral spirits or any similar petroleum solvent, hot alkaline wash or low pressure steam. If dried and cured the film of **TECTYL ML GREENLINE** can also be removed with Tectyl Biocleaner.

Features & Benefits

Superior Protection

Tectyl ML GREENLINE will protect against corrosion and will displace water where needed. With the low amount of VOC, Tectyl ML Greenline is also very efficient in use.

Strong penetration

With its strong penetration, Tectyl ML GREENLINE will protect the surface against corrosion, even in small seams and crevices.

Tectyl
PROTECTIVE PRODUCTS

PRODUCT INFORMATION



Trusted since 1930

Since 1930, Tectyl™ protective coatings have been extending the operational life of cars, trucks, buses and other vehicles and equipment. The Tectyl name is synonymous with quality coatings that are easy to apply, long-lasting and easy to remove when no longer required.

For more information on Tectyl products, programs and services please visit www.tectyl-europe.com

Typical properties

Typical property characteristics are based on current production. Whilst future production will conform to Tectyl specifications, variations in these characteristics may occur.

Tectyl ML GREENLINE	
Flash Point, PMCC [°C]	<0
Density @ 20°C [kg/ltr]	0,75
Nature of propellant	Propane /Butane
Recommended Dry Film Thickness over metal profile [microns]	40
Volatile Organic Compound Content of Concentrate ISO 11890-2 (10.4) [g/ltr]	342

This information only applies to products manufactured in the following location(s): Europe

Health & Safety

This product is not likely to present any significant health or safety hazards when properly used in the recommended application and good standards of personal hygiene are maintained. Reference is made to the Safety Data Sheet (SDS) which is available on request via your local sales office or via the internet <http://sds.valvoline.com>

Protect the environment

Comply with local regulations. Do not discharge into drains, soil or water.

Storage

Tectyl ML GREENLINE should be stored at temperatures between 10-35 °C. Shake before use! Under proper storage conditions Tectyl ML GREENLINE is best before 24 months after production date.

Caution

Adequate ventilation is required for cure and to ensure against formation of combustible liquid. THE PARTIALLY CURED FILM SHOULD NOT BE EXPOSED TO IGNITION SOURCES SUCH AS FLARES, FLAMES, SPARKS, EXCESSIVE HEAT OR TORCHES. Refer to The Safety Data Sheet for additional handling and first aid information.

Note

The addition of any product over or under this coating is not recommended. The use of additional coatings could result in chemical incompatibility, thus affecting the performance of this coating as stated in the Typical Properties section. If a primer, other than a Valvoline recommended product is required, written authorization must be obtained from Valvoline.

Replaces – TE071/01

™ Trademark of Valvoline, registered in various countries © 2017

All statements, information and data presented herein are believed to be accurate and reliable, but are not to be taken as a guarantee, an express warranty, or an implied warranty of merchantability or fitness for a particular purpose, or representation, express or implied, for which Ellis Enterprises B.V. and its affiliates assume legal responsibility.

Tectyl
PROTECTIVE PRODUCTS